



PO Box 437 MOUNT MARION, NY 12456 ~ 962 KINGS HIGHWAY, SAUGERTIES, NY 12477

PHONE (888) 528-7853 FAX (845) 246-2619

Website: [www.nesolite.com](http://www.nesolite.com)



TO WHOM IT MAY CONVERN

DATE: June 30, 2017

The test data from the average gradation of 325 we have produced is listed below!

MATERIAL SIZE: 325

<u>Sieve</u>	<u>% retained</u>
3/8"	0.0
#4	13.3
#8	32.5
#16	22.0
#30	12.2
#50	5.9
#100	3.8
Pan	10.3
Density (OD)	54 pcf
Moisture Content:	12.3%
Specific Gravity:	1.60

If you have any further questions, please do not hesitate to contact me.

  
*Ronald E. Vaughn*  
*Director of Technical Services*

cc: RV/file