



PO Box 437 MOUNT MARION, NY 12456 ~ 962 KINGS HIGHWAY, SAUGERTIES, NY 12477

PHONE (888) 528-7853 FAX (845) 246-2619

Website: www.nesolite.com



TO WHOM IT MAY CONVERN

DATE: June 30, 2017

The test data from our Greenlite based on the average data.

MATERIAL SIZE: Greenlite (# 300)

<u>Sieve</u>	<u>% retained</u>	<u>ASTM C331 Spec</u>
3/8"	0.0	0-2
#4	3.7	0-10
#8	32.2	15-35
#16	23.6	15-35
#30	13.2	5-20
#50	8.1	5-15
#100	5.1	5-15
Pan	14.4	8-20
Density @ 12%:	56.9 pcf	Max 70 pcf
Moisture Content:	12.3%	

This sample meets the specification limits above! If you have any further questions, please do not hesitate to contact me.

Ronald E. Vaughn
Director of technical Services

cc: RV/file